

AN EXCELLENT WAY TO PREPARE CONDUCTIVE GLASS USING A SIMPLE GLASS PLATE AIMING A PROMISING SOLAR CELL

Harsasi Setyawati, Handoko Darmokoesoemo, Hamami, Faidur Rochman, Ahmadi Jaya Permana

Department of Chemistry, Faculty of Science and Technology
Airlangga University, 60115 Indonesia
E-mail: harsasi85@gmail.com

Received 05 January 2017
Accepted 20 July 2017

ABSTRACT

The conductive glass is a solar cell main component. The thickness of TiO_2 acting as a semiconductor plays a primary role in the transmission, photoconductive properties, and the efficiency of solar cells. This research advances an excellent method to obtain a promising conductive glass for solar cells fabrication through coating a simple commercial soda lime glass by a thin layer of TiO_2 . The product described shows higher efficiency than that of fluorine thin oxide glass which is currently used in solar cells. Its application is expected to overcome the high cost of solar cells.

Keywords: excellent, conductive, glass, simple, thin layer, TiO_2 .

INTRODUCTION

Solar energy is one of the best alternatives of renewable energy resource because it is safe, clean and effective [1]. On other hand, its current efficiency is still poor and has to be improved. Many researchers work on inventing suitable techniques for the production of the best solar cell component [2 - 4]. Many experiments have been done to improve the efficiency of the solar cell since the discovery of the nanostructured dye-sensitized solar since the discovery of the nanostructured dye-sensitized solar cell (DSSC). One of the solutions is to prepare conductive glass through coating an affordable glass plate by a thin semiconductor layer. This approach provides the opportunity to have cheaper solar cells by using a small amount of materials and low-cost fabrication technologies [5, 6]. The aim of this study is to prepare conductive glass by deposition of a thin layer of titanium dioxide on a plate of simple commercial soda lime glass. The product expected can decrease the costs of fabricating solar cells.

EXPERIMENTAL

Titanium(IV) isopropoxide ($\text{Ti}(\text{OC}_3\text{H}_7)_4$) (TTIP), 4-(1,1,3,3-tetramethylbutyl) phenyl polyethylene glycol (Triton X-100), iodine (I_2), potassium iodide (KI), acetic acid (CH_3COOH), hydrochloric acid (HCl), ethanol ($\text{CH}_2\text{CH}_3\text{OH}$) and ether. Dye sensitizer used was rhodamine B were used in this study. FTO (*Fluorine doped Tin Oxide*) glass from *Latech scientific supply Pte. Ltd Singapore* (10 Ω , 25 x 25 x 3.2 mm), simple soda lime glass (25 x 25 x 1.2 mm), a graphite pencil and binder clips were also used.

The structure of the thin TiO_2 layer was characterized by XRD (X' pert PRO Diffractometer) and SEM (Carl zeiss EVO MA 10 English). The DSSC cell performance was followed by a multimeter Dekko using a potentiometer circuit. The solar irradiance was measured by Light Meter Krisbow KW06-288.

The procedures applied referred to:

- **Preparation of a glass plate using commercial soda lime glass**

Commercial soda lime glass of a thickness of 1.2 mm was cut to square plates of 25 mm x 25 mm size. They were sanded and coated with TiO_2 sol to produce a thin layer of titanium dioxide.

- **Preparation of TiO_2 sol for coating a glass plate**

A thin layer of titanium dioxide was deposited by the sol-gel method. 5 mL of triton X -100 were added to acetic acid and then transferred to 225 mL of ethanol while stirring for 3 min. 15 mL of TTIP dissolved in 1 mL of concentrated hydrochloric acid were added to the solution. The mixture was stirred for 2 h to form a sol [7].

- **Simple glass plate coating by TiO_2 sol**

Titanium dioxide sol was dropped onto the glass plate. The droplets were leveled through swiping the surface by another glass plate. The sample prepared was dried in an oven for 10 min at 80°C . The procedure described is performed three times on the same glass plate. Then the latter was calcinated for 2 h at 450°C [8]. The preparation procedure is illustrated in Fig. 1.

- **Performance of the conductive glass prepared in a solar cell**

The performance of the conductive glass prepared was tested by juxtaposing it to the FTO glass as a working electrode in a solar cell. Aiming this the both samples were immersed in 10^{-2} M rhodamine B as a dye sensitizer for 24 h. Thus they became ready to act as working electrodes. The corresponding counter electrodes were




Fig. 1. Preparation of conductive glass using a simple glass plate and a thin layer of TiO_2 .




Fig. 2. DSSC cells.

prepared in the following way. A homogeneous scratch of a graphite pencil was left on two other glass plates. They were left in contact with combustion soot until a homogenous surface was obtained. The counter electrodes were attached to the working electrodes and clamped with a binder clip (Fig. 2). An electrolyte solution containing I_2 dissolved in KI was dropped between each two electrodes. The DSSC cells thus obtained were connected to two multimeters to measure their current and voltage [2]. The working electrode acted as a cathode, while the counter electrode as an anode. At the same time, the sunlight intensity was measured by a light meter.

RESULTS AND DISCUSSION

The conductive glass developed in the course of this research is juxtaposed to FTO glass acting as working electrodes in a solar cell using rhodamine B as a dye sensitizer.

The diffractogram of the thin layer of TiO_2 shows three peaks at 25.2926° ; 37.9248° ; 48.1980° (Fig. 3).




Fig. 3. The diffractogram of TiO_2 thin layer deposited on a simple glass plate.




Fig. 4. SEM images of the surface of the thin TiO₂ layer deposited on simple glass plate (zoom 5000x).

It is compared to the diffractogram of anatase TiO₂ on the standard spectrum card JCPDS No. 88-1175 and 84-1286. Anatase TiO₂ has a larger surface area than TiO₂ rutile facilitating dye sensitizer attachment [10].

The thin TiO₂ layer obtained is characterized by SEM and the results are shown in Fig. 4. It is evident that surface pores are formed. The pore diameter is diverse – it ranges between 874.2 μm and 8,870 μm. The pores formed increase the surface area and contribute to the solar cell dye (Dye Sensitized Solar Cells) attachment. This condition is very advantageous because the increase of the dye attached to the semiconductor results in increase of solar cell capability to capture solar energy and generate a larger electric conversion [11].

Figs. 5 and 6 show the current and voltage obtained using both working electrodes. The current and voltage recorded on the conductive glass developed in the course




Fig. 5. Current vs time curve.




Fig. 6. Voltage vs time curve.

of this research have higher values from day to day than those found using FTO glass. The highest values of the current and the voltage refer to 48 mA and 0.5 V. This indicates that the glass advanced has a potential to be used as conductive glass in a solar cell.

Table 1. Performance of DSSC cells.

	Glass Type	Average		FF	Efficiency (%)
		Voc (V)	Isc (mA)		
TiO ₂	FTO	0.3552	0.0160	0.0995	0.00054
TiO ₂ - rhodamine B	FTO	0.4543	0.0400	0.1126	0.00194
TiO ₂	Simple Glass	0.3552	0.0120	0.4272	0.00173
TiO ₂ - rhodamine B	Simple Glass	0.4552	0.0064	0.6096	0.00169

Solar irradiance = 26.307 W/m²

Table 1 shows that the conductive glass developed produces Voc/Isc higher than that of FTO glass i.e. 0.3553 V / 0.0120 mA for TiO₂ and 0.4552 V/0.0064 mA for TiO₂-rhodamine B. The same is valid for the efficiency as well. The values estimated refer to 0.00173 % for TiO₂ and 0.00169 % for TiO₂-rhodamine B. These results verify that the glass obtained through deposition of a thin TiO₂ layer on a simple glass plate can be applied as conductive glass in a solar cell.

CONCLUSIONS

The research reported shows that the thin layer of titanium dioxide deposited on a plate of commercial soda lime glass plate has an anatase structure and pores providing a high surface area, which in turn facilitate dye sensitizer binding. The conductive glass described has an efficiency of 0.00169 %, which is higher than that of FTO glass.

Acknowledgements

The authors would acknowledge the research grant "Hibah Dosen Muda" sponsored by Faculty of Science and Technology of Airlangga University. They thank "PUPT (Penelitian Unggulan Perguruan Tinggi)" sponsored by RISTEKDIKTI (Kementerian Riset Teknologi dan Pendidikan Tinggi) for the generous funding and the Department of Chemistry at the Faculty of Science and Technology of Airlangga University Surabaya, Indonesia, for support and facilities.

REFERENCES

1. J. Zhou et al., Effect of Ag Powder and Glass Frit in Ag Paste on Front Contract of Silicon Solar Cells, *Procedia Engineering*, 94, 2014, 1-5.
2. D. Aradilla et al., Properties of nanometric and micro-metric multilayered films made of three conducting polymers, *Eurepean Polymer Journal*, 46, 12, 2010, 2222-2228.
3. A. Jarkov et al., Conductive polymer PEDOT:PSS back contact for CdTe solar cell, *Thin Solid Films*, 519, 21,2011, 7449-7452.
4. S. Jayaraman, D. Rajarathnam, M. Srinivasan, Formation of polythiophene multilayers on solid surfaces by covalent molecular assembly, *Materials Science and Engineering B*, 168, 1, 2010, 45-54.
5. A. Purwanto, H. Widiyandari, A. Jumari, Fabrication of high-performance fluorine doped-tin oxide film using flame-assisted spray deposition, *Thin Solid Films*, 520, 6, 2012, 2092-2095.
6. H. Surahman, Y.K. Krisnandi, J. Gunlazuardi, Preparation and Characterization of Transparent Conductive SnO 2-F Thin Film Deposited by Spray Pyrolysis: Relationship between Loading Level and Some Physical Properties, *Procedia Environmental Sciences*, 28, 2015, 242-251.
7. N. Fagnern et al., Effect of titanium tetraisopropoxide concentration on the photocatalytic efficiency of nanocrystalline thin films TiO₂ used for the photodegradation of textile dyes, *Journal of Physics and Chamistry of Solids*, 73, 12, 2012, 1483-1486.
8. R. Vijayalakshmi, V. Rajendran, Synthesis and characterization of nano-TiO₂ via different methods, *Arch. App.Sci.Res.*, 4, 2, 2012, 1183-1190.
9. H. Chang et al., Dye-sensitized solar cell using natural dyes extracted from spinach and ipomoea, *Journal of Alloys and Compounds*, 495, 2, 2010, 606-610.
10. C.M. Malengreaux et al., optimized deposition of TiO₂ thin films produced by a non-aqueous sol-gel method and quantification of their photocatalytic activity, *Chem. Eng. J.*, 195, 2012, 347-358.
11. H. Setyawati et al., Promising Dye Sensitizer on Solar Cell from Complexes of Metal and Rhodamine B, *Int. J. of Renewable Energy Research*, 5, 3, 2015, 694-698.